

# MasterEmaco® T 1060

Very rapid-setting cement-based concrete repair mortar

FORMERLY 10-60 RAPID MORTAR

## PACKAGING

50 lb (22.6 kg) polyethylene-lined bags  
3,000 lb (1,360 kg) bulk bags

## YIELD

0.43 ft<sup>3</sup> (0.012 m<sup>3</sup>) per 50 lb (22.6 kg)

- WHEN EXTENDED 50%:

0.57 ft<sup>3</sup> (0.016 m<sup>3</sup>)

- WHEN EXTENDED 100%:

0.77 ft<sup>3</sup> (0.022 m<sup>3</sup>)

## STORAGE

Store in unopened containers in cool, clean, dry conditions

## SHELF LIFE

- 50 LB BAGS:

1 year when properly stored

- 3,000 LB BULK BAGS:

3 months when properly stored

## VOC CONTENT

0 g/L less water and exempt solvents

## DESCRIPTION

MasterEmaco T 1060 is a one-component shrinkage-compensated very rapid-setting cement-based mortar. It is designed for repairing horizontal concrete surfaces where high early strength gain is required.

## PRODUCT HIGHLIGHTS

- Extra low permeability helps minimize chloride intrusion
- Very rapid-setting so that structures can be opened to vehicular traffic in 1 hour
- Low residual moisture, can be coated in as little as 4 hours
- Excellent resistance to freeze/thaw cycling
- Shrinkage compensated, minimizing cracking from drying shrinkage reducing stress at the bond line
- Can be extended up to 100% by weight providing higher yields
- Proprietary cement blend bonds to carbonated and noncarbonated concrete substrates

## APPLICATIONS

- Interior and exterior
- Horizontal surfaces
- Applications requiring high early-strength gain
- Structural concrete repairs
- Partial and full-depth repairs

## SUBSTRATES

- Concrete

## HOW TO APPLY

### SURFACE PREPARATION

#### CONCRETE

1. Concrete must be structurally sound and fully cured (28 days).
2. Saw cut the perimeter of the area being repaired into a square with a minimum depth of ½" (13 mm).
3. Refer to current ICRI Guideline no. 310.2R for surface prep requirements to permit proper bond.

#### REINFORCING STEEL

1. Remove all oxidation and scale from the exposed reinforcing steel in accordance with ICRI Technical Guideline No. 310.1R.
2. For additional protection from future corrosion, coat the prepared reinforcing steel with MasterProtect P 8100 AP.

**Technical Data**

**Composition**

MasterEmaco T 1060 is a blend of cement, graded aggregate, shrinkage-compensating agents, and set-control additives.

**Compliances**

- ASTM C 928

**Test Data**

The following results were obtained with a water / powder ratio of 5.5 pints (2.6 L) of water to 50 lbs (22.7 kg) of MasterEmaco T 1060 at 73° F (23° C).

PROPERTY	RESULTS	TEST METHOD
<b>Fresh wet density, lb/ft<sup>3</sup> (kg/m<sup>3</sup>)</b>	130 (2,082)	ASTM C 138
<b>Set time, min, at 72° F (22° C)</b>		ASTM C 191
Initial	16	
Final	28	
<b>Working time, min</b>	8	
<b>Length change, % (μstrain)</b>		ASTM C 928
Drying shrinkage	-0.05 (-500)	
Wetting expansion	+0.03 (+300)	
<b>Coefficient of thermal expansion, in/in/° F (cm/cm/° C)</b>	7.0 x 10 <sup>-6</sup> (12.6 x 10 <sup>-6</sup> )	CRD C 39
<b>Modulus of elasticity, psi (GPa)</b>	4.4 x 10 <sup>6</sup> (19.5)	ASTM C 469
<b>Rapid chloride permeability, coulombs</b>	< 300	ASTM C 1202
<b>Freeze/thaw resistance, % RDM, at 300 cycles</b>	100	ASTM C 666, (Procedure A)
<b>Scaling resistance, at 25 cycles</b>	0 rating; no scaling	ASTM C 672
<b>Slant shear bond strength, psi (MPa)</b>		ASTM C 882, modified <sup>1</sup>
1 day	2,300 (16)	
28 days	2,600 (18)	
<b>Splitting tensile strength, psi (MPa)</b>		ASTM C 496
1 day	400 (3)	
28 days	450 (3)	
<b>Flexural strength, psi (MPa)</b>		ASTM C 348
1 day	700 (5)	
28 days	850 (6)	
<b>Compressive strength, psi (MPa), 2" cubes</b>		ASTM C 109
1 hr	2,000 (14)	
1 day	4,000 (28)	
28 days	8,000 (55)	
<b>Compressive strength, psi (MPa), 3 by 6" cylinders, at 28 days</b>	7,400 (51)	ASTM C 39

<sup>1</sup>No bonding agent used; mortar scrubbed into substrate.  
 All application and performance values are typical for the material, but may vary with test methods, conditions, and configurations.

### MIXING

1. Precondition material to 70° F ±5° (21° C ±3°) before mixing.
2. Add 5½ pints (2.6 L) of potable water to the mixing container for each bag of MasterEmaco T 1060. If required, add the correct amount of aggregate to the mixer. Add the powder to the water while continuously mixing with a slow-speed drill and paddle, mortar mixer, or other forced action mixer.
3. Mix for a minimum of 3 minutes until fully homogeneous.

### AGGREGATE EXTENSION

1. For repair areas 2–4" (51–102 mm) in depth, the minimum recommended addition is 15–25 lbs (6.8–11.4 kg) of ¾" (10 mm) washed, graded, rounded, SSD, low-absorption, high-density aggregate per 50 lb (22.6 kg) bag.
2. For areas greater than 4" (102 mm) in depth, the minimum recommended addition is 25–50 lbs (11.4–22.6 kg) of ¾" (10 mm) washed, graded, rounded, SSD, low-absorption, high-density aggregate per 50 lb bag.
3. The maximum aggregate extension is 50 lbs (22.6 kg) of pea gravel per bag.
4. Aggregate must comply with the requirements of ASTM C 33.

### APPLICATION

1. After removing all standing water, thoroughly scrub a thin layer of bond coat into the saturated surface with a stiff-bristled broom or brush. Do not dilute the bond coat with water. Do not apply more of this bond coat than can be covered with mortar before the bond coat dries. Do not retemper the bond coat.
2. Immediately place the repair mortar from one side of the prepared area to the other. Work the material firmly into the bottom and sides of the patch to ensure good bond. Level the MasterEmaco T 1060 and screed it to the elevation of the existing concrete. Apply the appropriate finish.
3. Finish the completed repair, as required, taking care not to overwork the surface.
4. The recommended application range of MasterEmaco T 1060 is from 40 to 85° F (4 to 29° C). Follow ACI 305 and 306 for hot or cold weather.
5. A maximum of 15 minutes should be allowed to mix, place, and finish MasterEmaco T 1060 at 70° F (21° C).

### CURING

Cure with an approved curing compound compliant with ASTM C 309 or preferably ASTM C 1315.

### CLEAN UP

Clean tools and equipment with clean water immediately after use. Cured material must be removed mechanically.

### FOR BEST PERFORMANCE

- Minimum ambient, surface, and material temperature is 40° F (4° C) and rising.
- Do not mix longer than 5 minutes.
- Minimum application thickness is ½" (13 mm).
- Consult coating supplier for overcoating requirements.
- Do not mix partial bags.
- Do not add plasticizers, accelerators, retarders, or other additives.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit [www.master-builders-solutions.BASF.us](http://www.master-builders-solutions.BASF.us) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

---

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.basf.us](http://www.master-builders-solutions.basf.us), e-mailing your request to [basfbcst@basf.com](mailto:basfbcst@basf.com) or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,  
call ChemTrec® 1(800)424-9300.**

---

#### LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.